

GROMOV, M.I., TSYLEV, L.M.

"Non-Blast-Furnace Desulphurization of Cast-Iron,"
lecture given at the Fourth Conference on Steelmaking, A.A. Baikov, Institute of
Metallurgy, Moscow, July 1-6, 1957

137-58-5-9051D

Translation from: Referativnyy zhurnal, Metallurgiya, 1958, Nr 5, p 43 (USSR)

AUTHOR Gromov, M.I.

TITLE An Investigation of the Process of Desulfurization of Pig Iron in a Rotary Furnace (Issledovaniye protsessa desulfuratsii chuguna vo vrashchayushcheyseya pechi)

ABSTRACT: Bibliographic entry on the author's dissertation for the degree of Candidate of Technical Sciences, presented to Int-t metallurgii AN SSSR (Institute for Metallurgy, Academy of Sciences, USSR), Moscow, 1957

ASSOCIATION Int-t metallurgii AN SSSR (Institute for Metallurgy, Academy of Sciences, USSR), Moscow

1. Iron--Desulfurization 2. Furnaces--Applications

Card 1/1

Gromov M.I. 130-3-2/21
AUTHORS: Gromov, M. I., Tsylev, L.M., Zakunin, A.M., Kotov, V.I.
and Kaporulin, V. N.

TITLE: Desulphurization of pig iron outside the blast furnace.
(Vnedomennoye obesserivaniye chuguna).

PERIODICAL: Metallurg, 1958, No.3, pp.3-6 (USSR).

ABSTRACT: The authors give diagrams (Fig.1) to show the various methods tried in the USSR and abroad for the external desulphurization of pig iron with soda, calcium carbide or other solid reagents. They suggest that their comparative neglect is due mainly to their relative inefficiency and low productivity. The French IRSID method they criticize on the additional grounds that it could be difficult to effect on a large scale, that special arrangements would be required for trapping the lime dust produced, that the finely divided reagent would be difficult to obtain and that nitrogen is not available at many works. They go on to describe a method developed at the Novo-Lipetskiy metallurgical works in which the liquid metal is treated with lime in a rotating vessel, coke being added to maintain a reducing atmosphere. B. Provotorov, A. Nikitin and
Card 1/3 L. Sidorin participated in this work. Experiments

150-3-2/21

Desulphurization of pig iron outside the blast furnace.

showed that the desulphurization process is affected by the fluidity of the metal, the quantities of solids added per unit weight of metal, the sizing of the solids and the speed of rotation of the vessel. The internal diameter of the experimental vessels (Fig. 1) was 1050 mm and the length of the cylindrical part 1240 mm; one end was conical. With chrome-magnesite lining no build-up of slag on the walls or chemical disruption of the lining occurred. With speeds of rotation of 2.5 and 4.4 m/sec the sulphur content of the metal fell from 0.085 to 0.03-0.012%. The authors give a nomogram for determining the optimal speeds of rotation in relation to the viscosity of the metal and the vessel diameter, and this shows that the optimal speed for the experimental conditions was 9-10 m/sec which would have given more rapid desulphurization. The method is recommended to other works, the following being given as optimal conditions: lime with a minimal content of silica and carbon dioxide, under 1 mm in particle size and added in a quantity of 1% by weight of the iron; coke of particle size 1-3 mm to be added in a quantity of 0.3-0.5% of the weight of the iron; the entrance of slag or runner sand

Card 2/3

Desulphurization of pig iron outside the blast furnace. 12 - 5-5/62
into the vessel and the formation of encrustations on
the lining to be prevented. An editorial note says
that the Giprovoz organization is designing a 100-ton
capacity vessel.
There are three figures.

ASSOCIATION: Institut metallurgii AN SSSR i Novo-Lipetskiy
metallurgicheskiy zavod (Institute of Metallurgy
AS USSR and the New-Lipetsk Metallurgical Plant.

AVAILABLE: Library of Congress.

Card 3/3

SOV/180-59-3-5/43

AUTHORS: Gromov, M.I. and Tsylev L.M. (Moscow)

TITLE: On the Mechanism of Desulphurisation of Pig Iron with Solid Lime

PERIODICAL: Izvestiya Akademii nauk SSSR, Otdeleniye tekhnicheskikh nauk, Metallurgiya i toplivo, 1959, Nr 3, pp 25-28 (USSR)

ABSTRACT: The existing theories on the mechanism of the transfer of sulphur from slag to metal are discussed. In order to study the mechanism of desulphurisation of pig iron (solid pig iron - solid lime and liquid pig iron - solid lime) experimental work has been carried out. In the first series of experiments ignited lime balls were placed in a crucible, surrounded by crushed pig (0.08 - 0.1% S) and heated to various temperatures (600 to 900°C) for periods of 20 minutes to 3 hours. In the second series lime balls were dipped into molten pig iron and retained in it for periods from 1 second to 15 minutes. The surface of the lime balls was then analysed by petrographic and X-ray methods. It was found that in no case did the lime surface contain iron but only CaO, CaS and in the case of solid iron CaSO_4 , the amount of which was decreasing with increasing temperature at which the experiment was carried out. On the basis of the results

Card 1/2

SOV/180-59-3-5/43

On the Mechanism of Desulphurisation of Pig Iron with Solid Lime

obtained, the following mechanism of the desulphurisation with solid lime is postulated: in liquid metal, sulphur is present in the form of sulphur ions which are adsorbed on the surface of the lime, replacing oxygen in the crystal lattice:



As however, oxygen is more electronegative than sulphur, its bond with calcium should be stronger and probably some additional forces are necessary to replace it in the lattice with sulphur. It is thought that carbon has a weakening influence on the calcium oxygen bond. The apparatus used for the experiments for dipping lime balls into molten iron is shown in Fig 1. There is 1 figure and 5 references, 3 of which are Soviet and 2 English.

SUBMITTED: January 26, 1959

Card 2/2

GROMOV, M.I., kand.tekhn.nauk, Moskva.

Natural gas in metallurgy. Priroda 49 no.9:60-61 S '60.

(MIRA 13:10)

(Iron--Metallurgy)

(Gas, Natural)

ARTEMENKO, I.A.; GROMOV, M.I.; TSYLEV, L.M.

Technological processes for extracting concentrates for producing
thickeners. Biul.tekh.-ekon.inform. no.11:3-4 '60.

(MIRA 13:11)

(Ore dressing)

BOGDANOVICH, K.I.; ~~GROMOV, M.I.~~

New soda substitute for the desulfuration of pig iron. Trudy
Inst. met. no.12:16-19 '63. (MIRA 16:6)

(Desulfuration)
(Calcium manganese oxide)

GROMOV, M.I. (Moskva); SHUBEKO, P.Z. (Moskva); TSYLEV, L.M. (Moskva);
KOLESNIKOVA, L.L. (Moskva)

High speed magnetic roasting of iron ores in two-stage system
vortex chambers. Izv. AN SSSR. Met. i gor. delo no.1:15-19
Ja-F '64. (MIRA 17:4)

GROMOV, M. (M.)

"Distance," article published in Samoylet (Airplane), No. 1, Jan. 41, Moscow

M. Gromov, famous flyer and a "Hero of the Soviet Union," wrote a two-page article entitled "Distance" (of airplane flights) which appeared in the "Today and Tomorrow" section of the No. 1 issue of the magazine Samoylet, January 41. This is a popular article on the importance and possibilities of the long distance non-stop air flights. According to the author, the day is not too far off when it will be possible to make a non-stop flight around the earth in some 80-90 hours.

GROMOV, M.M., geroy Sovetskogo Soyuza, general-polkovnik aviatsii.

Participate in sport! Discussion with Air Force Colonel-General
M.M. Gromov, Hero of the Soviet Union. Voen.snan. 31 no.8:1 Ag '56.
(MLRA 9:11)

(Physical education and training)

GROMOV, M.^{M.} geroy Sovetskogo Soyusa.

Moscow - North Pole - United States. Kryl. rod. 8 no.7:14-15 J1 '57.
(Aeronautics--Flights) (MIRA 10:9)

DUZ', Petr Dmitriyevich; SEMENOV, V.A., prof., doktor tekhn.nauk, general-mayor, zasluzhennyy deystel' nauki i tekhniki, retsenzent; GROMOV, M.M., prof., general-polkovnik, retsenzent; ANOSHCHENKO, N.D., prof., retsenzent; BARKOVICH, D.M., kand. tekhn.nauk, red.; BELEVTSOVA, A.O., izdat.red.; ROZHIN, V.P., tekhn.red.

[History of aeronautics and aviation in the U.S.S.R.; period of the First World War, 1914-1918] Istoriia vozdukhoplavaniia i aviatcii v SSSR; period pervoi mirovoi voyny, 1914-1918 gg. Moskva, Gos.nauchno-tekhn.izd-vo Oborongiz, 1960. 298 p.
(Aeronautics--History) (MIRA 13:11)

GROMOV, Mikhail Nikolayevich, kand.ekon.nauk; TARARUKHIN, A., red.;
PAVLOVA, S., tekhn.red.

[How to ensure correct labor organization] Kak obespechit'
pravil'nuiu organizatsiiu truda. Moskva, Mosk.rabochii, 1960.
30 p. (MIRA 13:12)
(Moscow Province--Farm management)
(Moscow Province--Agricultural wages)

GROMOV, M.N., kand. ekonom. nauk; KALASHNIKOVA, V.S., red.; GUREVICH,
M.M., tekhn. red.

[How to shift to a new wage system on state farms] Kak pereiti na
novuiu oplatu truda v sovkhozakh. Moskva, Izd-vo sel'khoz. lit-ry,
zhurnalov i plakatov, 1961. 151 p. (MIRA 14:12)
(Agricultural wages)

LOZA, G.M., prof.; BUZILOV, Yu.T., dots.; GROMOV, M.I., dots.;
NIKIFOROV, M.A., dots.; FEFELOV, V.P., kand. ekon. nauk;
SINYUKOV, M.I., dots.; SAL'KOVA, A.D., dots.; GRADITSKIY,
P.A., dots.; TIKHONOVA, Ye.M., red.

[Practical aid for the organization and planning of produc-
tion on collective and state farms] Praktikum po organizatsii
i planirovaniu proizvodstva v kolkhozakh i sovkhozakh. Mo-
skva, Kolos, 1965. 526 p. (MIRA 18:5)

RUDENKO, A.M.; SPITSA A.I.; GROMOV, M.S.

Virusological characteristics of poliomyelitis in Dnepropetrovsk
Province. Vop. virus. 7 no.2:240-241 Mr-Apr '62. (MIRA 15:5)

1. Dnepropetrovskiy institut epidemiologii, mikrobiologii i gigiyeny.
(DNEPROPETROVSK PROVINCE—POLIOMYELITIS)

GROMOV, M.V.

Treatment of fractures of the upper part of the humerus in children.
Vest.khir.76 no.8:52-55 S '55 (MLRA 8:11)

1. Iz kliniki detskoy khirurgii (zav.prof. S.D.Ternovskiy) 2-go
Moskovskogo meditsinskogo instituta im. I.V.Stalina na baze detskoy
bol'nitsy im. prof. Filatova (glav.vrach M.N.Kalugina) Moskva,
120-b, per Obukha, d.6, kv.13.

(SHOULDER, fractures
in child, management)

(FRACTURES
shoulder, in child., management)

GROMOV, M.V., dotsent; SHALEVICH, M.A.

Rare case of diffuse angiomatosis of the lower extremity in association with congenital rib dislocation. Khirurgiya no.9: 106-107 '61. (RIB. 15:5)

1. Iz kliniki travmatologii i ortopedii (zav. - prof. V.A. Chernavskiy) II Moskovskogo gosudarstvennogo meditsinskogo Instituta imeni N.I. Pirogova i patologoanatomicheskogo otdeleniya 4-y Gorodskoy klinicheskoy bol'nitsy (glavnyy vrach G.F. Papko), Moskva.
(ANGIOMATOSIS) (EXTREMITIES, LOWER--DISEASES)
(RIBS--DISLOCATION)

GROMOV, M.V., dotsent

Alloplastic restoration of the ligament apparatus of the knee
joint. Nauch.trudy Chetv.Mosk.gor.klin.bol'. no.1:95-104 '61.
(MIRA 16:2)

1. Iz kliniki travmatologii i ortopedii (zav. klinikoy - prof.
Chernavskiy, V.A.) 2-go Moskovskogo gosudarstvennogo meditsinskogo
instituta imeni N.I. Pirogova (dir. - dotsent M.G. Sirotkina).
(KNEE---SURGERY) (LIGAMENTS---SURGERY) (SURGERY, PLASTIC)

GRONOV, M. V.

GRONOV, M. V.: "Enclosed fractures of the proximal portion of the shoulder in children and their treatment." Second Moscow State Medical Inst imeni I. V. Stalin. Moscow, 1956. (DISSERTATION For the Degree of Candidate in Medical Science.

So: Knizhnaya Letopis', No. 18, 1956

BUBENNIKOV, Aleksandr Vasil'yevich; GROMOV, M.Ya., prof., doktor
tekhn. nauk, otv. red.; SAGITULLINA, R.I., tekhn. red.

[Descriptive geometry; principal methods for projecting
geometric forms on a plane] Nachertatel'naia geometriia;
osnovnye metody proektirovaniia geometricheskikh form na
ploskosti. Moskva, Vses. sochnyi politekhn. in-t.
Lektsiia no.1. 1959. 46 p. (MIRA 16:4)
(Geometry, Descriptive)

BUBERNIKOV, Aleksandr Vasil'yevich; GROMOV, Mikhail Yakovlevich;
IVANOV, N.N., red.; OVSYANNIKOVA, Z.G., red. izd-va;
MURASHOVA, V.A., tekhn. red.

[Problems in descriptive geometry] Sbornik zadach po na-
chertatel'noy geometrii. Moskva, Vysshaya shkola, 1963.
282 p. (MIRA 1741)

BUDEBNIKOV, Aleksandr Leonovich; 1907-1977, 1. Vol., 1. izd. 1977.
mos., prof., dok. ped.

[Descriptive geometry; point, straight line, plane,
methods of modification of drawings, curves] Nachertat-
sel'naya geometriia; točka, priamá, ploskost', spó-
soby preobrazovaniia chertezhei, krivye linii. Moskva,
Vses. zapchnyi pol'tekhn. inst., 1977. 354 p.
(21.02.18:6)

GROMOV, N.

Out-of-town session. Zdrav. Belor 5 no.2:69 F '59. Zdrav. Belor
5 no.2:69 F '59. (MIRA 12:7)
(WHITE RUSSIA--MEDICAL MYCOLOGY)

GROMOV, N.D.

With Krivoy Rog steel smelters. Metallurg 6 no.7:37-39 J1 '61.
(MIRA 14:6)
(Krivoy Rog--Metallurgical plants)

GROMOV, N.D.

Progressive practices are being shared with all steelmakers.
Metallurg 6 no.10:37 0 '61. (MIRA 14:9)
(Steel--Metallurgy)

S/028/62/000/010/001/001
D201/D308

AUTHORS: Gromov, N.D., Kasatkina, N.M. and Kaplan, A.S.

TITLE: Thermobimetals

PERIODICAL: Standartizatsiya, no. 10, 1962, 16-21

TEXT: The authors describe the principles underlying the proposed new specification of standards related to bimetallic strips. The new standard specification consists of the letters TB (TD) followed by a four-digit number. The first two digits correspond to the magnitude of the specific bending coefficient multiplied by 100. The third digit shows that the value of the nominal specific electrical resistance of the strip belongs to one of the groups of properties specified in a table of standards. The fourth digit indicates that the maximum operating temperature belongs to one of the groups of the same table. In the proposed new standard specification the heading 'Technical requirements' standardizes the sensitivity and electrical resistance of the material only. All other physical properties of the bimetal and of its separate components are indicated.

Card 1/2

Thermobimetals ...

3, 125, 12, 000, 125, 002, 001
D201/D308

rad in an appendix to the specification which, for every standard type of bimetal, sets the limits of its specific bending factor A in $1/^\circ\text{C}$, the sensitivity M , $10^{61}/^\circ\text{C}$ and of the specific resistivity ρ , $\text{ohm}\cdot\text{mm}^2/\text{m}$. A method for sensitivity testing is also included. The instrument for determining the specific bending coefficient has not yet been fully developed. The standard specification discussed here is to replace the two existing standard specifications for bimetal strips GOST 5193-50 (GOST 5193-50) and GOST 5198-50. There are 4 tables and 4 figures.

Card 2/2

GROD OV, Nikolay (M. Ilyevich), TONKOV, V. I., 1964. Laureat Gos. premii
rebezcent

[Intensification of steel production] Intensifikatsiya
proizvodstva stali. Moskva, Izd-vo "Metallurgiya,"
1964. 158 p. (MIRA 18:1)

GROMOV, N.G.

DECEASED

1961/I

c1960

See ILC

AGRICULTURE/Mushrooms

~~GHOMOV, N. I.~~

Viability and virulence of *Treponema pallida* at low temperature
in a cadaver. Sbor.nauch.rab.Bel.nauch.-iusl.kozhno-ven.inst.
4:251-253 '54 (MIRA 11:7)
(*TREPONEMA PALLIDA*)

USSR/Pharmacology and Toxicology. Chemotherapeutic Preparations
Antibiotics

V-7

Abs Jour : Ref Zhur - Biol., No 15, 1958, No 71276

Author : Prokopchuk A.Ya., Gromov N.I., Raskina R.I.

Inst : Belorussian Scientific Research Dermatovenereal Institute

Title : Experience in the Treatment and Prophylaxis of Pyogenic
Diseases of the Skin with Triple Dyes and Antibiotics
(Synthomycin, Biomycin and Terramycin)

Orig Pub : Sb. nauchn. rabot. Belorussk. n.-i. kozhno-venerol. in-t,
1957, 5, 116-119

Abstract : No abstract

Card : 1/1

GROMOV, N.I., kand.med.nauk; MARIUPOL'SKIY, R.M., ordinator

Treatment of suppurative skin diseases with staphylococcus
antiphagin. Zdrav.Belor. 3 no.10:59-60 0 '57. (MIRA 13:6)
(SKIN--DISEASES)

PEVZNER, Ye.S.; RASKINA, R.I.; GROMOV, N.I.

Our paste for washing and protecting the hands as a means of preventing dermatitis and suppurative skin diseases among metal workers. Sbor. nauch.rab.Bel.nauch.-issl.kozhno-ven.inst. 6:211-214 '59. (MIRA 13:11)
(HAND--CARE AND HYGIENE)
(OINTMENTS)

GROMOV, N.I., kand.med.nauk; PETRUSHA, I.S., vrach; SOSLAND, R.D., vrach

Terramycin in the prevention and treatment of suppurative skin diseases. Sbor.nauch.rab.Bel.nauch.-issl.kozhno-ven.inst. 6:276-278
'59. (MIRA 13:11)

(TERRAMYCIN)
(SKIN--DISEASES)

GROMOV, N.I.; RASKINA, R.I.

Control of suppurative skin diseases in the industrial and peat
enterprises of the White Russian S.S.R. Sbor.nauch.rab.Bel.nauch.-
issl.kozhno-ven.inst. 6:365-367 '59. (MIRA 13:11)
(WHITE RUSSIA--PEAT INDUSTRY--HYGIENIC ASPECTS)
(SKIN--DISEASES)

GROMOV, N.I.

Two cases of Leiner's erythroderma desquamativum. Sbor.nauch.rab. Bel.
nauch.-issl.kozhno-ven.inst. 6:368-369 '59. (MIRA 13:11)
(SKIN--DISEASES)

OROMOV, N.I.

Case of trichosporosis nodosa. Sbor.nauch.rab.Bel.nauch.-issl.kozhno-
ven.inst. 6:370-371 '59. (MIRA 13:11)

(HAIR--DISEASES)

(MEDICAL MYCOLOGY)

GROMOV, N. K. Cand. Tech. Sci.

Dissertation: "Rational System of Heat Supply for Cities." Power Engineering Institute
imeni G. M. Krzhizhanovskiy, Acad Sci USSR, 24 Apr 47.

CC: Yechernyyaya Moskva, Apr, 1947 (Project #17226)

GROMOV, N.K.

Initials

USSR/Engineering - Heating
Power Supply

Nov 49

"Some Results in Moscow District Heating and
Power Supply and Tasks for the Immediate Future,"
N. K. Gromov, Cand Tech Sci, 4 pp

"Elek Stants" No 11

Describes Moscow stations and pipe systems which
supply about 550 dwellings, over 100 schools and
hospitals, over 300 institutions, and over 80 in-
dustrial enterprises. However, all these repre-
sent only about 15% of possible users of district
heating, and system is still being extended. In-
cludes two sketches.

156T26

F

651. CLOSED THERMAL SYSTEM FOR URBAN HEATING. Gromov, N.
(Elektricheskie Stantsii (Pwr Stns), Aug. 1949, vol. 20, 21-27).

The author describes a modified closed system using local automatic boosters and indicates advantages of reliability and flexibility.

p

ASS. SLA METALLURGICAL LITERATURE CLASSIFICATION

GROMOV, N.K., inzhener; GERBKO, A.A., inzhener.

Twenty-five years of Soviet central heating systems. Gor.khoz.Mosk. 23 no.11:
11-17 N '49. (MLRA 6:11)

(Moscow--Heating from central stations) (Heating from central stations--
Moscow)

GROMOV, N.K.

Basic problems of operating the heat supply system of Moscow. Gor.khoz.Mosk.
25 no.10:6-10 0 '51. (MLHA 6:11)

1. Gromov, N.K., glavnyy inzhener Teploseti Mosenergo.
(Moscow--Heating from central stations)
(Heating from central stations--Moscow)

LANIN, I.S.; KHARITON, M.I.; GROMOV, N.K., redaktor.

[Control of corrosion in heating networks] Opyt bor'by s korroziei v teplo-
vykh setiakh. Pod red. N.K.Gromova. Moskva, Gos.energ.izd-vo, 1953. 51 p.
(MLBA 6:10)

(Corrosion and anticorrosives) (Heating from central stations)

GRIGOROV, N. K. - LUK'YANOV, V. I. - FILIPOV, M. F.

Moscow - Heating from Central Stations

Practical systems for district heat supply in Moscow.
Gor. khoz. Mosk. no. 1, 1953

9. Monthly List of Russian Accessions, Library of Congress, May 1953. Unclassified.

GROMOV, N.K., kandidat tekhnicheskikh nauk.

Basic problems in the dependable operation of city central heating systems. Gor.khoz.Mosk. 28 no.6:21-24 Je '54.(MLRA 7:7)
(Moscow--Heating from central stations) (Heating from central stations--Moscow)

NIKOLAY KONSTANTINOVICH

SOKOLOV, Yefim Yakovlevich, professor, redaktor; GROMOV, Nikolay Konstantinovich;
SAFONOV, Aleksandr Petrovich; PAKSHVER, V.B., redaktor; PRIDKIN,
A.M., tekhnicheskiy redaktor.

[Operation of heating systems] Eksploatatsiia teplovykh setei. Pod
red. E. Ia. Sokolova. Moskva, Gos.energ.izd-vo, 1955. 352 p.
(Heating) (MLRA 9:1)

AID P - 2907

Subject : USSR/Electricity
Card 1/2 Pub. 26 - 4/32
Author : Gromov, N. K., Kand. Tech. Sci.
Title : Immediate problems in automation of district heating systems
Periodical : Elek.sta, 7, 14-18, J1 1955
Abstract : The author reports on the conditions and operation of district heating networks and on "chaotic" hot water distribution. The article deals with different types of automatic inlet regulators used for heating hot water and ventilation systems. Their diagrams are given. The article further reports on experiments made by the District Heating Network of the Moscow Power System and the Engineering and Construction Institute im. Kuybyshev. The All-Union Technical Institute im. Dzerzhinskiy was put in charge of working out new methods for the installation of automatic regulators. Five diagrams.

AID P - 2907

Elek. sta, 7, 14-18, J1 1955

Card 2/2 Pub. 26 - 4/32

Institution : None

Submitted : No date

G. P. N. K.

GROMOV, N.K., kand.tekhn.nauk; SOKOLOV, Ye.Ya., doktor tekhn.nauk.

District heating in the U.S.S.R. on the anniversary of the
October Revolution. Elek.sta. 28 no.11:71-74 N '57. (MIRA 10:11)
(Heating from central stations)

SENKOV, F.V., kand.tekhn.nauk; KONOVALOVA, A.P., inzh.; KONONOVICH, Yu.V.,
inzh.; YELISEYEVA, A.S., tekhnik; POLYAKOV, V.F., tekhnik; GROMOV,
N.K., kand.tekhn.nauk, retsenzent; VOL'FKOVICH, M.Ye., retsenzent;
CHABROV, I.M., red.

[Regulation of the daily allowance of heat supply to apartment
houses and public buildings; scientific report] Rezhim avtochno-
go regulirovaniia otpuska tepla zhilym i obshchestvennym zdaniyam;
nauchnoe soobshchenie. Pushkin, Akad.kommun.khoz.im.K.D.Pamfilova,
1959. 73 p. (MIRA 13:5)

(Heating from central stations)

SOV/96-59-4-3/21

AUTHOR: Gromov, N.K., Candidate of Technical Sciences
TITLE: Measures to Reduce the Cost and Construction Time of Heating Systems (Meroprivatiza po snizheniyu stoimosti i strokov stroitel'stva teplovykh setey)

PERIODICAL: Teploenergetika, 1989, No 4, pp 17-20 (USSR)

ABSTRACT: One of the main reasons why, in many cases, district heating does not give the designed fuel economy is that the heat output of the turbines is not fully used because of the slow rate of construction of heating systems. This occurs because a number of technical and organizational problems are unsolved, particularly because of the high cost of heating systems. It is important that the lag in the construction of heating systems should be quickly overcome. The influence of pipework and other equipment is first considered. At the present time there is a very heavy demand for steel piping and great economy in its use is important. A most effective way of economizing steel pipe is to cut down the wall thickness. Possibilities in this direction are somewhat limited by the restricted range of tube available. One of the

Card 1/4

NOV/96-59-4-3/21

Measures to Reduce the Cost and Construction Time of Heating Systems

reasons why tube wall thicknesses have to be kept up is because of corrosion troubles. Bituminous protective coatings have been relatively successful in cutting down corrosion troubles. Other types of protective paint have not been so good. Pipes should be wrapped with paper to prevent damage to the protective covering in transport. The design organisations should pay more attention to cathodic protection. Since steel tubes are in such short supply and require careful protection it may be advantageous to use non-metallic tubes such as asbestos cement, glass or plastic. In particular the first results with asbestos cement and glass tubes are promising. The method of installation and the type of heat insulation used have important effects on the cost of construction of heating systems. Several promising new heat insulating materials have recently been developed notably, cellular ceramics and thermo-peat. Such materials should be carefully tried out in practice. It is considered justifiable not to provide thermal insulation on the return line in large heating mains of 800-1000 mm diameter

Card 2/4

001/96-59-4-3/21

Measures to Reduce the Cost and Construction Time of Heating Systems

even where fuel is expensive. This question should be specially considered in each particular case. Sometimes, in order to avoid waste, heating lines have been laid that were not big enough to provide adequately for future development and parallel lines have then had to be laid at much greater overall cost. This kind of trouble is best overcome by avoiding selectivity in the provision of heat supply and by providing heat supplies simultaneously on a fully developed scale for each particular district. In order to ensure economy at consumers' installations they must be provided with appropriate instruments and automatic control equipment but unfortunately the output of automatic control equipment is quite inadequate. Various other types of equipment that are also in short supply are mentioned. Special efforts should be made to rationalise and mechanise the construction of heat supply lines, primarily by the use of factory produced components.

Card 3/4

SOV/96-59-4-3/21

Measures to Reduce the Cost and Construction Time of Heating Systems

To avoid disputes general standards should be developed
for the inspection and acceptance of heating systems.

ASSOCIATION: Mosenergo

Card 4/4

14(6)

SOV/91-59-5-2/27

AUTHOR: Gromov, M.K., Engineer

TITLE: The Technical Foundations of Thermofication of Moscow
(Tekhnicheskiye osnovy teplofikatsii Moskvy)

PERIODICAL: Energetik, 1959, Nr 5, pp 3-8 (USSR)

ABSTRACT: This is an account of recent developments in the Moscow thermofication system, and covers such matters as thermal equipment of power plants, water and steam networks, hydraulic and thermal regimes of water networks, technical equipment of networks and thermal points, organization of service, and a few recommendations on what should be done in order to secure the best results from the whole thermofication system. The annual output of heat delivered in 1958 to the Moscow consumers reached 9 million "Mkcal". Extensive thermofication has reduced the attending personnel by 10,000. Since the end of WWII, the old AP-25 and AP-25 turbines (25,000 kw, 29 atm, 400°C) were

Card 1/4

001/01-50-5-2/27

The Technical Foundations of Thermofication of Moscow

gradually replaced by high-pressure VT-25 turbines (25,000 kw, 90 atm, 400°C). They are planned to be supplemented with 50,000-100,000 kw turbines; soon. Old boilers will be replaced by gas-fired, peak boilers developed by the VTI. The principal pumps are 1000-1200 ton/hour pumps. The principal pre-heaters have capacities of 500-550 m³. The water for the heating networks is now heated up to 150°C, which results in elimination of water accumulators in residential houses. Water is fed in under 9-11 atm. Over 3000 water elevators, the TETs pumping stations and four substations, two of which are fully automatic, ensure the proper circulation. Radius of hot water network has grown to 7 km. Networks of separate TETs are interconnected. The maximum radius of hot steam (3-6 atm) increased to 3 km. About 45% of used steam returns to TETs. The Moscow heating network has underground pipes,

Card 2/4

307/91-59-5-2/27

The Technical Foundations of Thermofication of Moscow.

of two-pipe type. The VTI and the plant "Krasnyy Stroitel'" have developed a new type of twin-pipe line, consisting of two asbestos-cement pipes put upon each other, with a mineral wadding in between. They tested well in dry grounds. The Mospodzemstroy successfully uses the prefabricated blocks containing an asbestos-cement and steel pipes, with a mineral wadding in between. The automatic relay regulator developed by the ORGRES have found wide application on the thermal mains. The Moskovskiy energeticheskii institut (Moscow Institute of Energetics) has developed a device called "Dis-petcherskiy raport" (Dispatcher's Report), which, using only two telephone wires, communicates 6 parameters of steam from any point of the steam network. This device is undergoing modification aimed at enabling it to automatically inspect 50 control points at one time. The municipal thermal net-work is subdivided into 6 districts,

Card 3/4

SCV/01-59-5-2/27

The Technical Foundations of Thermofication of Moscow.

operated and controlled by the Dispatcher Point
of the Teplocet'. There are 3 tables.

Card 4/4

GROMOV, N.K.

Production tasks of the seven-year plan for the development of district heating systems in Moscow. Gor.khoz.Mosk. 33 no.2:14-18 F '59.
(MIRA 12:3)

1. Glavnyy inzh. Upravleniya teploseti "Mosenergo".
(Moscow--Heating from central stations)

GROMOV, N.K.

Prevention of corrosion in a heat supplying network. Energetik 9
no.8:34 Ag '61. (MIRA 14:8)
(Heating from central stations) (Pipelines--Corrosion)

GROMOV, N.K., red.; DUKHOVNAYA, S.M., red.; FRIDKE, L.M., tekhn. red.

[Single-pipe systems of heat distribution networks] Odnorubnye
sistemy teplovykh setei; sbornik statei. Moskva, Gosenergoizdat,
1962. 207 p. (MIRA 15:5)

(Heating from control stations)

MITTEL'MAN, L.M., kand.tekhn.nauk; GROMOV, N.K., inzh.

Concerning S.E.Shitsman's article "Methodology for accounting for
and standardization of technical and economic indices of thermal
electric power plants." Elek. sta. 33 no.8:89-91 Ag '62.
(MIRA 15:8)

(Electric power plants—Standards) (Shitsman, S.E.)

GROMOV, N. K.

Concerning the rinsing-out of the thermal networks. Energetik
10 no.8:32 Ag '62. (MIRA 15:10)

(Electric power plants)

GROMOV, N.K., inzh.

Development of centralized heating in Moscow. Teploenergetika
11 no.11:7-12 N '64. (MIRA 11:12)

1. Teploset' Moskovskogo rayonnogo upravleniya energeticheskogo
khozyaystva.

VUKALOVICH, M.P.; GROMOV, N.K.; IMBRIITSKIY, M.I.; KARTOSHNIK,
M.D.; KOBRINA, R.B.; LEONOVA, A.Ya.; TROYANSKIY, Ye.A.;
MANUYLOV, P.N.; SHUKHER, S.M., red.

[Heat engineer's handbook] Spravochnaia knizhka teplo-
tekhnika. Izd.2., perer. i dop. Moskva, Energiia, 1964.
287 p. (MIRA 17:12)

AKSENOV, Mikhail Alekseyevich. Prinimal uchastiye GROMOV, N.K.,
kand. tekhn. nauk; SINEL'NIKOVA, L.N., red.

[Heating networks; sources and consumers of thermal energy.
Installation, maintenance, and repair of networks] Teplovye
seti; istochniki i potrebiteli tepla. Ustroistvo, obsluzhiva-
nie i remont setei. Moskva, Energiia, 1965. 351 p.
(MIRA 18:9)

MAI'TSEV, B.G.; GROMOV, N.N., kandidat ekonomicheskikh nauk, retsenzent;
MORIN, L.A., inzhener, retsenzent; EIKHENVAL'D, A.V., kandidat
ekonomicheskikh nauk, redaktor; MATVEYEVA, Ye.N., tekhnicheskii
redaktor.

[Planning in a foreman's section] Opyt planirovaniia na uchastke
mastera. Moskva, Gos. nauchno-tekhn. izd-vo mashinostroit. lit-ry,
1954. 81 p. (MIRA 8:1)
(Machinery industry--Accounting)

STARCHENKO, D.I., kandidat tekhnicheskikh nauk; GROMOV, N.P., redaktor;
MIKHAYLOVA, V.V., tekhnicheskii redaktor

[Comprehensive groove designing of shaped profiles] Razvernutaya
kalibrovka fazonnykh profilei. Moskva, Gos.nauchno-tekhn.izd-vo
lit-ry po cherno i tsvetnoi metallurgii, 1952. 247 p.(MLBA 8:10)
(Rolling mills)

GROMOV, N.P., kandidat tekhnicheskikh nauk, nauchnyy redaktor; NEPOMNYA-SHCHIY, N.V., redaktor; PETROVA, N.S., tekhnicheskiiy redaktor

[Press working of metals; collection of articles] Obrabotka metallov davleniem; sbornik statei. Moskva, Gos. nauchno-tekhn. izd-vo lit-ry po chernoi i tsvetnoi metallurgii. No.3. 1954. 267 p. (MLRA 7:10)
(Rolling (Metalwork))

TARNOVSKIY, I.Ya., doktor tekhnicheskikh nauk, professor; GROMOV, N.P.,
redaktor; STARODUBTSEVA, S.N., redaktor; ATTOPOVICH, M.K., tekhnicheskii redaktor

[Deformation during the plastic molding of metal; forging and
rolling] Formoizmeneniye pri plasticheskoi obrabotke metallov;
kovka i prokatka. Moskva, Gos. nauchno-tekhn. izd-vo lit-ry po
chernoi i tsvetnoi metallurgii, 1954. 534 p. (MLRA 7:9)
(Deformations (Mechanics)) (Forging)
(Rolling (Metalwork))

POLUKHIN, Petr Ivanovich; GROMOV, N.P., redaktor; GOLYATKINA, A.G.,
redaktor; TARASHENKO, Z.K., tekhnicheskiiy redaktor.

[Rolling and shaping of I-beams] Prokatka i kalibrovka dvu-
tavrovyykh balek. Moskva, Gos.nauchno-tekhn. izd-vo lit-ry po
cherno i tsvetnoi metallurgii, 1956.175 p., 137 diagrams.
(Girders) (Rolling (Metalwork)) (MIRA 9:5)

GROMOV, N.P., kandidat tekhnicheskikh nauk, redaktor; VALOV, N.A., redaktor,
~~ATTOPOVICH~~, M.K., tekhnicheskii redaktor.

[Press working of metals; a collection of articles] Obrabotka metallov
davleniem; sbornik statei. Moskva, Gos. nauchno-tekhn. izd-vo lit-ry
po cherno i tsvetnoi metallurgii. No.4, 1956. 239 p. (MLRA 9:4)
(Rolling (Metalwork))

OROMOV, N.P., kand. tekhn. nauk; GOLOVANENKO, S.A., kand. tekhn. nauk;
~~KASATKIN, N.M., inzh.~~

New thermostatic bimetals. Vest. elektroprom. 27 no.8:32-33 Ag '56.
(MIRA 10:9)

1. Institut pretsizionnykh splavov Tsentral'nogo nauchno-issledovatel'-
skogo instituta chernoy metallurgii.
(Thermostat) (Metals)

157-1957-12-25488

Translation from: Referativnyy zhurnal, Metallurgiya, 1957, Nr 12, p 334 (USSR)

AUTHORS: Gromov, N. P., Il'ichev, A. I., Kasatkin, N. M.

TITLE: Manufacture of Alloys With a Rectangular Hysteresis Loop
(Proizvodstvo splavov s pryamougol'noy petley gisterezisa)

PERIODICAL: Sb. tr. Tsentr. n.-i. in-t chernoy metallurgii, 1956, Nr 15, pp 259-273

ABSTRACT: Research on alloys was conducted in three areas: a) creation of a texture in Fe-Ni alloys, b) utilization of the texture of certain alloys by means of thermomagnetic treatment, c) utilization of the increase in residual inductance of some alloys with a reduction in the thickness of the strip to 5μ . Basic technological operations and peculiarities are given for the production of strips composed of three alloys: 65NP, 45NKP, and 34NKMP. Magnetic properties of strips of various thickness, prepared from these alloys, are also shown.

P. N.

Card 1/1 1. Alloys-Development 2. Alloys-Applications 3. Alloys-
 Manufacture

GROMOV, N.P., kand. tekhn. nauk, nauchnyy red.; VALOV, N.A., red.
----- izd-va; ISLENT'YEVA, P.G., tekhn. red.

[Rolling practice and pipe manufacture] Prokatnoe i trubnoe pro-
izvodstvo; sbornik statei. Moskva, Metallurgizdat, 1958. 384 p.
(MIRA 15:9)

(Rolling (Metalwork)) (Pipe mills)

GRL M 01, N, P

KOROLEV, Andrey Andreyevich, kand.tekhn.nauk, dots.; KUZ'MIN, A.D., kand.
tekhn.nauk, retsenzent; DVINYANINOV, S.A., inzh., retsenzent;
GROMOV, N.P., kand.tekhn.nauk, red.; OSIPOVA, L.A., red.izd-va;
EL'KIND, V.D., tekhn.red.

[Rolling mills; construction and design] Prokatnye stany; konstruk-
tsiya i raschet. Moskva, Gos. nauchn.-tekhn.izd-vo mashinostroit.
lit-ry, 1958. 450 p. (MIRA 11:4)
(Rolling mills)

SOV/126-6-5-9/43

AUTHORS: Borodkina, M.M., and Gromov, H.P.

TITLE: Study of the Texture of a 50% Fe-50% Ni Alloy in the Form of Strip of Various Thicknesses (Izucheniye tekstury splava 50% Fe-50% Ni v vide lenty razlichnoy tolshchiny)

PERIODICAL: Fizika Metallov i Metallovedeniya, 1958, Vol 6, Nr 5, pp 819 -- 824 (USSR)

ABSTRACT: The deformation and recrystallisation textures of strip of various thicknesses of the alloy 50NP (Permalloy) was studied by the pole figure method. Strip of thickness 0.05, 0.02, 0.01 and 0.005 mm was obtained by hot rolling without intermediate annealing. Two series of X-ray photographs, in which the specimen was turned through 10° between each exposure, were used to construct pole figures taken at a vertical and horizontal position to the rolling direction. The texturegraphs were taken by a Laue-type camera in a Mo-irradiation. For the study of the texture of different layers, the strip specimen was electrolytically polished. The most pronounced orientations were found to be (110) [112], (112) [111] and (236) [535].

On annealing a strip of 0.05 mm thickness, a distinct

Card1/3

SOV/126-6-5-9/43

Study of the Texture of a 50% Fe-50% Ni Alloy in the Form of Strip of Various Thicknesses

cubic recrystallisation texture, (001) [100], forms. The difference in deformation texture between strip of 0.005 mm and 0.05 mm thickness consists in the orientation (110) [112] being less pronounced and the number of disorientated crystals being greater in the thinner strip (see Figure 1). A decrease in strip thickness from 0.5 to 0.005 mm leads to gradual disappearance of recrystallisation texture (see Figure 4). The method of deformation influences the deformation texture and the effect of recrystallisation texture disappearance in a very thin strip (see Figure 8). The reason for the disappearance of recrystallisation texture appears to be the part played by the surface layers of a very thin strip, which are characterised by a weakening in the orientation (110) [112] and by an increase in the number of disorientated crystallites (see Figure 9). Figures 2 and 3 represent pole figures of deformed strip of 0.05 and 0.005 mm thickness, respectively, and Figures 5 and 7 pole figures of annealed strip of 0.05 mm and 0.003 mm thickness, respectively.

Card2/3

SOV/126-6-5-9/43

Study of the Texture of a 50% Fe-50% Ni Alloy in the Form of Strip
of Various Thicknesses

There are 9 figures and 5 references, 3 of which are
Soviet, 1 German and 1 English.

ASSOCIATION: Institut pretsizionnykh splavov TsNIICHM
(Institute of Precision Alloys of TsNIICHM)

SUBMITTED: January 31, 1957

Card 3/3

TABLE I BOOK EXPLANATIONS 307/340
 Moscow. Tsentral'nyy nauchno-issledovatel'skiy institut Chernoy metallurgii.
 Institut pretsizionnykh splavov

Prezisionnyye splavy (Precision Alloys) Moscow, Metallurgizdat, 1959. 265 p.
 (Series: Itsi; Sbornik zakonov, v. 22) 2,153 copies printed.

Additional sponsoring Agency: USSR. Gosudarstvennyy planovyy komitet

Ed.: B. I. Gerasimov; Ed. of Publishing House: Ye. I. Levitskiy; Tech. Ed.:
 P. G. Izrael'skiy.

PURPOSE: This collection of articles is intended for technical personnel
 and scientific workers in the metallurgical, instrument-manufacturing,
 and electrical-equipment-manufacturing industries. It may also be
 useful to students of schools of higher technical education.

COVERAGE: This collection of articles presents the results of studies of
 precision alloys made in recent years by the Central Scientific
 Research Institute of Ferrous Metallurgy (Central Scientific
 Institute of Ferrous Metallurgy). The properties of these alloys
 which can be achieved in the form of castings and wrought materials
 and alloys and their use in the design of springs are discussed. Analyses of
 electrical resistance and thermal expansion and the effect of
 irradiation on properties of alloys are considered. Problems
 connected with the determination of magnetic susceptibility and with
 rolling of bimetallic strips are reviewed. An analysis of alloys used
 in manufacturing high-temperature transducers and strain gauges is
 presented. No personalities are mentioned. References follow several
 of the articles.

Prezisionnyye, A. L., and B. A. Solov'yev. See Alloy for Instrument
 Parts 52

Belomestnyy, A. S., B. P. Belomestnyy, and V. A. Sol'tva. Utilization of the
 Bismuth Alloy for Making Drive Springs 57

Buravskiy, M. M., A. A. Gulyayevskiy, and V. A. Sol'tva. Structural
 Transformation of the Bismuth Alloy in the Range of Hot-Deformation
 Temperatures 71

Buravskiy, M. M., B. G. Melnikov, and V. A. Sol'tva. On the Problem of
 Cold Working of the Bismuth Spring Alloy 81

Sol'tva, V. A., and I. M. Rusanov. Effect of Molybdenum on Properties
 of the Bismuth (Bismuth) Alloy 91

Chernov, P. G. Bismuth Alloys Used for Elastic Sensing Elements 105

Portnov, A. E. The Modified Bismuth (B) Alloy for Spiral
 Springs for Vedic Mechanisms 111

Fedorov, L. M., and V. I. Rabin. Investigation of the Dependence of
 Anomalous Magnetization on the Loading of Iron-Aluminum Alloys with
 Silver Composition 121

Shtayn, V. G., and S. P. Gromov. Study of the Boiling of Bimetallic
 Strips in Boiling 134

Besovskiy, B. V., and L. L. Zolotarev. Methods of Short-Time Testing of
 Alloys Used for Electrical Sensing Elements 139

Al'tman, O. B., O. V. Lysotskiy, and V. A. Sol'tva. Determination
 of Magnetic Susceptibility of a Thin Wire Made of Low-Magnetic Im-
 purity 149

Artishevskiy, M. A., S. S. Vasil'yev, O. V. Lysotskiy, and Ye. P.
 Sojuzskiy. Effect of Neutron Irradiation on Electrical Resistance
 of Self-Ordering and Aging Alloys 159

Aysenkov, I. L. On the Problem of the Nature of the Strain in Alloys 177

Telyatnik, O. P. High-Resistance Alloy Used for Strain Gauges 183

Telyatnik, O. P. Alloys for High-Temperature Transducers 193

Besovskiy, B. V. On the Problem of the Electrical-Resistance Anomaly
 of the Bismuth Alloy 205

Besovskiy, B. V., and B. A. Besovskiy. Electrical Properties of Bismuth
 and Iron-Chromium-Aluminum Alloys 215

18(0)

PHASE I BOOK EXPLOITATION

SOV/2316

Akademiya nauk SSSR. Institut nauchnoy i tekhnicheskoy informatsii

Metallurgiya SSSR, 1917-1957; [t.] II (Metallurgy in the USSR, 1917 - 1957; Vol 2) Moscow, Metallurgizdat, 1959. 813 p. Errata slip inserted. 3,000 copies printed.

Ed. (Title page): I. P. Bardin, Academician; Ed. (Inside book): G. V. Popova; Tech. Ed.: P. G. Isent'yeva.

PURPOSE: This book is intended for metallurgists.

COVERAGE: The articles in this collection present historical data on the achievements of Soviet metallurgy, both ferrous and nonferrous, during the period 1917-1957. Advances in theory and practical application are thoroughly discussed. Many of the articles describe the present status of individual branches of metallurgy and give an idea of what may be expected in the future. Advances made in other countries are also discussed. The articles are accompanied by a large number of references. For further coverage, see Table of Contents.

Card 1/15

2

Metallurgy in the USSR (Cont.)

SOV/2316

TABLE OF CONTENTS:

Tselikov, A. I., Corresponding Member, USSR Academy of Sciences; Ye. S. Rokotyan, Doctor of Technical Sciences; N. P. Gromov, Candidate of Technical Sciences. (Ts NIIMASH and TsNIChM) Production of Rolled Stock

3

The authors present a historical review of the production of rolled stock in czarist Russia and the Soviet Union from 1721 to 1957. Developments in rolling technique and in the design of rolling mills for various purposes are discussed.

Yermolayev, N. F., Engineer; and P. K. Teterin, Candidate of Technical Sciences. (TsNIChM) Production of Steel Tubes

38

The article briefly outlines the history of steel-tube production in the USSR (beginning in 1893) and in other countries. The main methods of manufacturing seamless and welded steel tubular products at various Soviet and non-Soviet plants are described. There is some discussion of equipment.

Card 2/25

2

67768

18.7500
18.5110

SOV/126-8-5-21/29

AUTHORS: Borodkina, M.M., and Gromov, N.P.

TITLE: Study of Deformation and Recrystallization Textures of
an Iron-Nickel Alloy⁶ (48% Ni) in Relation to the
Degree of Deformation⁶ in Cold Rolling¹⁶

PERIODICAL: Fizika metallov i metallovedeniya, Vol 8, 1959, Nr 5,
pp 761-769 (USSR)

ABSTRACT: The alloy was made in an induction furnace and had the
following composition (wt.%): 47.75% Ni, 0.03% C,
0.55% Mn, 0.22% Si, 0.007% S, remainder iron. As a
result of forging and hot rolling a strip of 6 mm
thickness was obtained. By means of cold rolling the
annealed isotropic cold-rolled material, strips of the
alloy to be investigated were obtained, of approximately
50 μ thickness, with a reduction of between 11 and 99.4%,
and of 5 μ thickness, with a reduction of between 73.7
and 99.92%. The initial thickness of the rolled
material was between 19 μ and 6 mm (Table 1). Rolled
materials of various thickness without preferential
orientation were obtained by cold working with a
reduction not exceeding 60% and subsequent annealing at
950 °C. The hot-rolled annealed strip of 6 mm thickness ✓

Card
1/4

67768

SOV/126-8-5-21/29

Study of Deformation and Recrystallization Textures of an Iron-Nickel Alloy (48% Ni) in Relation to the Degree of Deformation in Cold Rolling

was also isotropic. The isotropy of the rolled material was verified by X-ray photographic and ionization methods. Annealing was carried out in a vacuum container (10^{-2} mm Hg) at 1100 °C for one hour; cooling was carried out at the rate of 100 °C/hour down to 600 °C; thereafter the container was cooled in air. Measurement of magnetic properties was carried out by a ballistic method. For the study of texture, besides the X-ray photographic method an X-ray ionization method with construction of quantitative pole figures was applied. Recording of intensity during exposure for the construction of entire pole figures was carried out by means of a texture attachment to the apparatus URS-50I (Ref 2). The intensity for a standard specimen free from texture, made from powder of the alloy under investigation and having an absorption factor identical with that of the investigated specimen, μt (μ - coefficient of linear absorption, t - thickness of the specimen) was taken as unity. Standard specimens were ✓

Card
2/4

67768

SOV/126-8-5-21/29

Study of Deformation and Recrystallization Textures of an
Iron-Nickel Alloy (48% Ni) in Relation to the Degree of
Deformation in Cold Rolling

also used for determination of corrections associated with drop in intensity with increase in the angle of deflection of the specimen. Figs 1 and 2 are X-ray patterns of specimens deformed to various degrees of reduction and of the same specimens after annealing at 1100 °C; the thickness of the specimens in Fig 1 is 50 μ and that in Fig 2, 5 μ . Figs 3 and 5 are pole figures of deformed (upper row) and annealed (lower row) strips; the thickness of strip in Fig 3 is 50 μ and that in Fig 5 is 5 μ . Fig 4 shows orientations of the texture of Fe-48% Ni alloy. The results of measurements of magnetic properties of the annealed specimens of 50 μ thickness were found to be in good agreement with the change in texture (Table 2). The authors arrive at the following conclusions: 1) as the degree of deformation increases a change in the intensity ratio of the orientations takes place. 2) after annealing a cubic recrystallization texture is observed only when as a result of deformation the texture with the intense

Card
3/4

67768

SOV/126-8-5-21/29

Study of Deformation and Recrystallization Texture of an
Iron-Nickel Alloy (48% Ni) in Relation to the Degree of
Deformation in Cold Rolling

components (110) $[\bar{1}\bar{1}2]$ and (110) $[3\bar{3}5]$ is formed, which corresponds to a deformation of 99.0%. Further increase in deformation leads to a weakening of the orientations (110) $[\bar{1}\bar{1}2]$ and (110) $[3\bar{3}5]$, and after annealing, to a weakening of the cubic recrystallization texture (100) $[001]$ and a fall in magnetic properties. 3) Not only the texture of the surface layers but also an excessive degree of deformation affects the cubic texture of a strip of 5 μ thickness. 4) The nature of the strip texture change of a Fe-Ni alloy (48% Ni) with increase in degree of deformation appears to indicate that the formation and growth of recrystallization nuclei during annealing takes place in an orientated manner.

There are 5 figures, 2 tables and 15 references, of which 5 are Soviet, 3 German, 6 English and 1 French. ✓

Card
4/4

ASSOCIATION: TsNIICHM

SUBMITTED: January 10, 1959

ADRIANOVA, V.P.; ANDREYEV, T.V.; ARANOVICH, M.S.; BARSKIY, B.S.; GROMOV, N.P.;
GUREVICH, B.Ye.; DVORIN, S.S.; YERMOLAYEV, N.F.; ZVOLINSKIY, I.S.;
KABLUKOVSKIY, A.F.; KAPKLOVICH, A.P.; KASHCHENKO, D.S.; KLIMOVITSKIY,
M.D.; KOLOSOV, M.I.; KOROLEV, A.A.; KOCHINEV, Ye.V.; LESKOV, A.V.;
LIVSHITS, M.A.; MATYUSHINA, N.V.; MOROZOV, A.N.; POLUKAROV, D.I.;
RAVDEL', P.G.; ROKOTYAN, Ye.S.; SMOLYARENKO, D.A.; SOKOLOV, A.N.;
USHKIN, I.N.; SHAPIRO, B.S.; EPSHTEYN, Z.D.; AVRUITSKAYA, R.F., red.
izd-va; KARASEV, A.I., tekhn.red.

[Brief handbook on metallurgy, 1960] Kratkii spravochnik metallur-
ga, 1960. Moskva, Gos.nauchno-tekhn.izd-vo lit-ry po chernoi i
tsvetnoi metallurgii, 1960. 369 p. (MIRA 13:7)
(Metallurgy)

POLUKHIN, Petr Ivanovich; FEDOSOV, Naum Maksimovich; KOROLEV, Andrey Andreyevich; MATVEYEV, Yuriy Mikhaylovich; SMIRNOV, V.S., prof., doktor tekhn.nauk, retsenzent; LAUR, G.K., retsenzent; GROMOV, N.P., dotsent, kand.tekhn.nauk, red.; GOROBINCHENKO, V.M., red. izd-va, DOBRYNINskaya, L.V., tekhn.red.

[Rolling mill practice] Prokatnoe proizvodstvo. Moskva, Gos. nauchno-tekhn.isd-vo lit-ry po chernoi i tsvetnoi metallurgii, 1960. 966 p. (MIRA 13:10)

1. Zamestitel' glavnogo inzhenera Magnitogorskogo metallurgicheskogo kombinata (for Laur).
(Rolling (Metalwork))

ZAROSHCHINSKIY, Mikhail Leont'yevich; FOLUKHIN, F.I., prof., doktor
tekhn. nauk, retsenzent; GRUMOV, N.P., prof., retsenzent;
FEDOSOV, N.M., prof., retsenzent; VAGIN, A.A., red. izd-va;
DOBUZHINSKAYA, L.V., tekhn. red.

[Technological principles of rolling mill design] Tekhnologichesk
skie osnovy proektirovaniia prokatnykh stanov. Moskva,
Metallurgizdat, 1962. 443 p. (MIRA 15:12)
(Rolling mills--Design and construction)

POLUKHIN, Petr Ivanovich, prof., doktor tekhn. nauk; GRDINA, Yu.V.,
prof., ~~doktor tekhn.~~ nauk; ZARVIN, Yevgeniy Yakovlevich, prof.;
GROMOV, N.P., prof., nauchnyy red.; GOFLOBINCHENKO, V.M., inzh.,
red. izd-va; ATTOPOVICH, M.K. [deceased], tekhn. red.

[Rolling and heat treatment of railroad rails] Prokatka i termi-
cheskaia obrabotka zheleznodorozhnykh rel'sov. [By] P.I. Polukhin
i dr. Moskva, Metallurgizdat, 1962. 510 p. (MIRA 16:2)
(Rolling (Metalwork)) (Railroads--Rail)

S/776/62/000/025/007/025

AUTHORS: Gromov, N. P., Zusman, Sh. I., Agaronik, V. Ya., Barkaya, D. S.

TITLE: On the lengthwise uniformity of the resistance of an extremely thin wire.

SOURCE: Moscow. Tsentral'nyy nauchno-issledovatel'skiy institut chernoy metallurgii. Sbornik trudov. no. 25. Moscow, 1962. Pretsizionnyye splavy. pp. 104-116.

TEXT: This paper reports the results of an experimental investigation, performed at the TsNIChM (Central Scientific Research Institute of Ferrous Metallurgy), intended to develop a methodology and construct equipment for the continuous inspection of the uniformity of the electrical resistance (ER) of extremely thin wires in the source of their motion. The problem is of the greatest importance for a variety of calculating and telemechanical devices in which the uniformity of the electrical resistance of potentiometer wire is a decisive element in determining the accuracy of measurements and telemetered information. The equipment newly constructed was used for the determination of the uniformity of the resistance of Ni-Cr wire 20-50 μ in diam. The experimental equipment comprises an idling feed spool and motor-driven take-up spool, between which the wire is guided by textolite guide rollers while in contact with a pair of spaced-apart contact rollers made of stainless steel

Card 1/3

On the lengthwise uniformity of the resistance S/776/62/000/025/007/025

with a Cr-plated surface. Diam of the contact rollers is 50 mm, that of the guide rollers 20 mm. A braking load is applied to the feed spool. Measurements can be made at contact distances of 1 m or 0.5 m. The linear velocity of the wire is 23-25 m/min. The resistance measurements were performed by means of a DC bridge of the type MBV (MVU) 49, a high-speed potentiometer of the type БП102 (BP102), and various auxiliary equipments. The theory of the dependence of the ER of the wire on the mechanical stresses prevailing therein is briefly outlined for given values of the Poisson coefficient and the Young modulus of elasticity. The results of an experimental illustrative test are shown graphically, illustrating the linear variation of the dependence up to the elastic limit for a 0.04-mm diam Ni-Cr wire. The conditions necessary to avoid any plastic bending stresses that may arise in contact with the guide and contact rollers are specified. Problems arising from the characteristics of the measuring equipment, the contact equipment, and the deformations of the wire while passing through the contact equipment, and the verification of the functioning of the entire equipment are discussed. It is found that the method and the equipment adopted here are suitable for the continuous measurement of the uniformity of the ER of micron wire along its length in the course of its motion. It is established that the degree of uniformity of the ER becomes less favorable with decreasing thickness of the wire. It is shown that cold-hardened wire exhibits a significantly better uniformity of the ER along its length as compared with

Card 2/3

On the lengthwise uniformity of the resistance

S/776/62/000/025/007/025 .

wire that has been subjected to heat treatment. The source of the impairment of the uniformity in the latter is attributed primarily to the quenching of the wire in the furnace system. It is shown that significant impairments in the uniformity of the ER of a wire along its length can be produced by careless unwinding and rewinding.

Card 3/3

GROMOV, N.P.; ZUSMAN, Sh.I.; AGARONIK, V.Ya.; BARKAYA, D.S.

Uniformity of resistance along the length of extremely thin wire.
Sbor. trud. TSNIICHM no.25:104-116 '62. (MIRA 15:6)
(Electronic apparatus and appliances--Testing)
(Electric resistance)

GROMOV, N. P.; KASATKIN, N. M.; KAPLAN, A. S.

Laminated metals. Standartizatsiia 26 no.10:16-21 0 '62.
(MIRA 15:10)

(Laminated metals)

GROMOV, N. P.; KAL'MENEV, A. A.

Effect of tension on the position of the neutral cross-section
during rolling. Izv. vys.ucheb.zav.; Chernomet 7. no. 5:81-84
'64. (MIRA 17:5)

1. Moskovskiy vecherniy metallurgicheskiy institut.